



High Quality Custom Displays



Say it Big!



Brand Building



Indoor and Outdoor Banners



Special Event Experts


MediaOne JetFlag Fire Certificate



FROM : DIVERSIFIED TESTING LABS

FAX NO. : 3362271175

Apr. 03 2009 01:37PM P1



DIVERSIFIED

TESTING LABORATORIES, INC.

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 3, 2009

Mr. Jason Bartusick
MEDIA ONE
DIGITAL IMAGING SOLUTIONS, LLC
7211 Garden Grove Blvd.
Suite D
Garden Grove, CA 92841

Reference: Laboratory Test Report
Lab Identification No. 9484
Invoice No. 21858 (Attached)

Dear Mr. Bartusick:

One (1) fabric sample, identified as **ECO FLAG 117 FR**, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237. Flame Resistance, Small Scale Test. The results are as follows:

<u>Specimen Number</u>	<u>After Flame Time (sec)</u>		<u>Char Length (in)</u>	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	4.1	3.7
2	0.0	0.0	4.9	3.6
3	0.0	0.0	5.0	4.6
4	0.0	0.0	5.5	3.1
5	0.0	0.0	4.2	2.9
Avg.	0.0	0.0		

The sample submitted, in its original state, **meets** the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett


BEP/mr
Attachment



FROM : DIVERSIFIED TESTING LABS

FAX NO. : 3362271175

Apr. 03 2009 01:38PM P2



DIVERSIFIED
TESTING LABORATORIES, INC.

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 3, 2009

Mr. Jason Bartusick
MEDIA ONE
DIGITAL IMAGING SOLUTIONS, LLC
7211 Garden Grove Blvd.
Suite D
Garden Grove, CA 92841

Reference: Laboratory Test Report
Lab Identification No. 9484
Invoice No. 21858 (Attached)

Dear Mr. Bartusick:

One (1) fabric sample, identified as **ECO FLAG 117 FR**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2004 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame (seconds)</u>	<u>Weight Loss (percent)</u>
1	0.0	21.73
2	0.0	26.88
3	0.0	17.64
4	0.0	27.88
5	0.0	27.59
6	0.0	22.19
7	0.0	22.89
8	0.0	28.33
9	0.0	21.27
10	0.0	18.48
AVG.	0.0	23.49

The fabric sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett


BEP/mr
Attachment



FROM : DIVERSIFIED TESTING LABS

FAX NO. : 3362271175

Apr. 03 2009 01:38PM P3



DIVERSIFIED
TESTING LABORATORIES, INC.

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 3, 2009

Mr. Jason Bartusick
MEDIA ONE
DIGITAL IMAGING SOLUTIONS, LLC
7211 Garden Grove Blvd.
Suite D
Garden Grove, CA 92841

Reference: Laboratory Test Report
Lab Identification No. 9484
Invoice No. 21858 (Attached)

Dear Mr. Bartusick:

One (1) fabric sample, identified as **SOLVO FLAG 100 FR-WOS**, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237. Flame Resistance, Small Scale Test. The results are as follows:

<u>Specimen Number</u>	<u>After Flame Time (sec)</u>		<u>Char Length (in)</u>	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	6.0	5.4
2	0.0	0.0	5.4	4.4
3	0.0	0.0	5.5	3.5
4	0.0	0.0	6.0	3.7
5	<u>0.0</u>	<u>0.0</u>	5.7	4.8
Avg.	0.0	0.0		

The sample submitted, in its original state, **meets** the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett


BEP/mr
Attachment



FROM : DIVERSIFIED TESTING LABS

FAX NO. : 3362271175

Apr. 03 2009 01:38PM P4



DIVERSIFIED

TESTING LABORATORIES, INC.

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 3, 2009

Mr. Jason Bartusick
MEDIA ONE
DIGITAL IMAGING SOLUTIONS, LLC
7211 Garden Grove Blvd.
Suite D
Garden Grove, CA 92841

Reference: Laboratory Test Report
Lab Identification No. 9484
Invoice No. 21858 (Attached)

Dear Mr. Bartusick:

One (1) fabric sample, identified as SOLVO FLAG 100 FR-WOS, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2004 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame (seconds)</u>	<u>Weight Loss (percent)</u>
1	0.0	17.73
2	0.0	23.00
3	0.0	19.10
4	0.0	19.67
5	0.0	10.80
6	0.0	14.01
7	0.0	12.74
8	0.0	14.16
9	0.0	19.64
10	0.0	18.81
AVG.	0.0	16.97

The fabric sample submitted meets the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett


BEP/mr
Attachment



FROM : DIVERSIFIED TESTING LABS

FAX NO. : 3362271175

Apr. 03 2009 01:38PM P5



DIVERSIFIED

TESTING LABORATORIES, INC.

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 3, 2009

Mr. Jason Bartusick
MEDIA ONE
DIGITAL IMAGING SOLUTIONS, LLC
7211 Garden Grove Blvd.
Suite D
Garden Grove, CA 92841

Reference: Laboratory Test Report
Lab Identification No. 9484
Invoice No. 21858 (Attached)

Dear Mr. Bartusick:

One (1) fabric sample, identified as **ECO DISPLAY 210 FR+W**, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237. Flame Resistance, Small Scale Test. The results are as follows:

Specimen Number	After Flame Time (sec)		Char Length (in)	
	Length	Width	Length	Width
1	0.0	0.0	5.5	4.1
2	0.0	0.0	3.7	4.0
3	0.0	0.0	5.1	3.4
4	0.0	0.0	3.7	4.5
5	0.0	0.0	3.1	4.8
Avg.	0.0	0.0		

The sample submitted, in its original state, **meets** the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment